



GRAFIGAST LEATHER LOOK FILMS

REFERENCE L03 – TUNDRA

Released on the 1st of September 2013



Description

The Graficast leather look film reference L03 – Tundra (available in black (L0302), beige (L0350), brown (L0352) and burgundy (L0354)) is a soft structured cadmium-free glossy PVC film with a leather effect. The film is provided with a pressure-sensitive permanent acrylic adhesive. This adhesive is protected by a high-quality silicone paper.

Composition

- Film : structured multi-layered cast PVC film with a leather effect
- Adhesive : transparent permanent pressure-sensitive solvent-based acrylic adhesive, with a high resistance against UV-radiation, chemical products and humidity.
- Backing paper : siliconised white PE-coated paper of 130 gr/m²

Application

Graficast leather look films can be used for indoor and outdoor applications. Thanks to their exceptional smoothness and good deformability these films are also perfectly suited for vehicle wrapping. When applying the structured films, it is important that the right techniques are used for heating the material. More "tips & tricks" on the application of the structured Graficast films can be found on our website (www.grafityp.com).

Product advantages

The Graficast leather look films make your design look like real leather.

Product specifications

Technical properties at a relative humidity of 50 ± 5 % and a temperature of 23 ± 2°C.

		Test method	Result	
			L0302	L0350-L0352-L0354
1.	Thickness¹ Thickness vinyl Thickness vinyl + glue + backing paper	Din53370 Din53370	220 µm 400 µm	
2.	Elongation at break² In production-length direction In cross direction	Din53455 Din53455	> 80% > 80%	> 30% > 30%
3.	Dimensional stability³	Finat 14	< 0.20 mm	
4.	Degree of gloss Minimum (measuring angle 20°)	Din67530	not measurable because of the structure of the material	
5.	Adhesion strength⁴ After 20 minutes After 24 hours	Finat 1 Finat 1	15 N/25mm 17 N/25mm	
6.	Quickstick⁵	Finat 9	12 N	
7.	Expected outdoor life span⁶	-	5 years	
8.	Temperature range At application At use	- -	+5°C to +40°C -45°C to +115°C	
9.	Colour back print	-	neutral	
10.	Flammability If applied on aluminium, glass, steel = self-extinguishing			

Storage instructions

All Graficast materials always need to be stored in their original packing and with the original protection flanges. Especially for cast films it is important that they are stored vertically. These films are softer than calendered films and consequently more sensitive to pressure marks when they are stored horizontally, resting on their own weight. In order to avoid any loss of quality, the Graficast materials should also be stored in suitable conditions, that is at a temperature between 10 and 20°C, and a relative humidity of 50%.

Under these conditions, the Graficast leather look materials can be stored up to two years.

Remarks

- In order to achieve an optimal result, we advise you to clean the surface with isopropanol and/or to use a low-tack application tape !
- The colour of the Graficast vinyls may come off slightly because of over-pigmentation, but as the film is coloured in the mass, this will have no influence on the UV-resistance and the eventual colour of the vinyl.
- As the colour of the film can differ slightly for each production run, we advise you not to use films with different batch numbers in one single and critical job. The number to be taken into consideration for this purpose consists of the first 5 numbers of the 7-digit batch number.
- In order to remove the film again, it should be heated thoroughly in order to prevent adhesive transfer. Due to the structure of the material, the film can tear while being removed.

Important

The information, mentioned in this product data sheet, is based upon tests that were executed by Grafityp, and that we consider to be reliable. The information always represents an average, a minimum or a maximum value, and should be considered as such. It is only given for your information, and does not give any guarantee. It is up to the end user to decide whether or not the product is suited for his particular application.

1)
The thickness of the Graficast materials may vary slightly. The indicated value is an average value, obtained from a series of measurements. With structured materials, the deviation from the guide value is larger than with even materials.

2)
The elongation at break of the Graficast materials may vary slightly. The indicated value is a minimum value, obtained from a series of measurements.

3)
The dimensional stability is the shrinkage of the unprinted material in mm. This value is measured by applying the film on aluminium (10x10cm), and placing it in a hot-air oven at 70°C for 48 hours (= Finat 14 Method, adjusted according to our own internally developed procedure). The indicated value is a maximum value, obtained from a series of measurements.

4)
The adhesion strength is measured on glass, and this after 20 minutes and after 24 hours. The film is removed again in an angle of 180° and at a speed of 300 mm/min. The indicated value is an average value, obtained from a series of measurements.

5)
The "Quickstick" is the direct adhesion strength, measured on glass. The indicated value is an average value, obtained from a series of measurements.

6)
The expected outdoor life span refers to outdoor use under Central European conditions and to vertical applications. Non-vertical application can reduce the life span up to 50%. The expected life span of our films is based upon professional application on a dry, degreased and suitable background. Tropical conditions, or the use near chemical emission, may have a detrimental effect on the life span. The life span can also differ, depending on the colour (due to the pigmentation).
For more detailed information we also refer to our general "Grafiprint Warranty Certificate" and to our "General Terms and Conditions of Sale and Delivery".